

PRODUCT DATA

3 03 62 13 **Non-Metallic
Non-Shrink Grouting**

CONSTRUCTION GROUT

**General construction, mineral-aggregate
nonshrink grout****Description**

Construction Grout is a noncatalyzed, multi-purpose construction grout containing mineral aggregate.

Yield

One 50 lb (22.7 kg) bag of Construction Grout mixed with 1.15 gallons (4.35 L) of water (flowable mix) provides approximately 0.45 ft³ (0.013 m³) of mixed grout.

Packaging

50 lb (22.7 kg) multi-wall paper bags

Color

Concrete gray when cured

Shelf Life

1 year when properly stored

Storage

Store in unopened bags under clean, dry conditions.

Features

- Concrete gray color (after curing)
- No organic accelerators, including chlorides or other salts
- Can be extended with clean, well-graded coarse aggregate
- Hardens free of bleeding when properly placed

Benefits

- Blends in with surrounding concrete
- Will not corrode reinforcing steel
- Fills large voids without additional mix water
- Provides high effective bearing area for proper support and load transfer

Where to Use

APPLICATION

- Normal loads for columns and baseplates
- Bedding grout for precast panels
- Repairing of cavities resulting from ineffective concrete consolidation
- Caulking concrete pipe
- Backfilling, underpinning foundations, and pressure grouting of slabs needing alignment
- General construction applications
- Damp pack applications

LOCATION

- Interior or exterior

How to Apply**Application**

For aggregate extension guidelines refer to Appendix MB-10: Guide to Cementitious Grouting.

Mixing

By using the minimum amount of water to provide the desired workability, maximum strength will be achieved. Whenever possible, mix the grout with a mechanical mixer. Either a mortar mixer or an electric drill with a paddle device is acceptable. Put the measured amount of water into the mixer, add grout, then mix till a uniform consistency is attained. Do not use water in an amount or a temperature that will cause bleeding or segregation.

Curing

Cure all exposed grout shoulders by wet curing for 24 hours and by applying a recommended curing compound compliant with ASTM C 309 or preferably ASTM C 1315.

For Best Performance

- Contact your local representative for a pre-job conference to plan the installation.
- Construction Grout is designed for the 50 to 90° F (10 to 32° C) application temperature range. Consult your BASF representative when applying outside this range. Use cold and hot weather concreting practices (ACI 305 and ACI 306) when grouting within 10° F (6° C) of these minimum and maximum temperature ranges.
- To ensure optimum performance of Construction Grout, place at a plastic or flowable consistency and at ambient temperatures of 50° F (10° C) and above.
- For best results, allow a minimum of 1" (25 mm) vertical clearance under baseplates when placing Construction Grout.
- Do not use Construction Grout where it will come in contact with steel designed for stresses above 80,000 psi (552 MPa). Use Masterflow® 816, Masterflow® 1205, or Masterflow® 1341 post-tensioning cable grouts.

CONSTRUCTION GROUT

Technical Data

Composition

Construction Grout is a noncatalyzed hydraulic cement-based grout containing mineral aggregate.

Compliances

- CRD C 621 and ASTM C 1107, Grade C, at flowable or plastic consistency
- City of Los Angeles Research Report Number RR 23137

Typical Properties

Mixed Grout Data* (Flowable Mix)

PROPERTY	VALUE
Approximate Water, gal (L)	1.15 (4.35)
Initial set, hrs, at 70° F (21° C)	6
Final set, hrs, at 70° F (21° C)	8

*At a constant percent of water, consistency will vary with temperature. Final set takes place in approximately 8 hours at a flowable consistency and 70° F (21° C).

Test Data

PROPERTY	RESULTS	TEST METHODS
Flow, %, 5 drops	126 – 145	ASTM C230
Volume change, %, flowable consistency, after 28 days	0.08	ASTM C 1090
Compressive strength, psi (MPa)		ASTM C 942, according to ASTM C 1107
	Consistency	
	Flowable¹	Plastic²
	Stiff³ (damp pack)	
1 day	1,500 (10)	—
3 days	5,000 (34.5)	6,000 (41.4)
7 days	6,000 (41.3)	7,000 (48.3)
28 days	7,000 (48.0)	8,500 (58.6)
	10,000 (69.0)	

¹ 140% flow on flow table, ASTM C 230, 5 drops in 3 seconds

² 100% flow on flow table, ASTM C 230, 5 drops in 3 seconds

³ 40% flow on flow table, ASTM C 230, 5 drops in 3 seconds

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

- Do not add plasticizers, accelerators, retarders, or other additives unless advised in writing by BASF Technical Services.
- The surface to be grouted should be clean, strong, and roughened to CSP 5 – 9 according to ICRI Guideline 03732 to permit proper bond. For freshly placed concrete, consider using Liquid Surface Etchant (see Form No. 1020198).
- Do not place Construction Grout in lifts greater than 6" (152 mm) unless the product is extended with aggregate to dissipate hydration heat.
- Where precision alignment and severe service, such as heavy loading, rolling, or impact resistance are required, use metallic-reinforced, noncatalyzed Embeco® 885 grout. If the amount of impact resistance needed is not great enough to require metallic reinforcement, use natural-aggregate, Masterflow® 928.
- The water requirement may vary with mixing efficiency, temperature, and other variables.
- The concrete surfaces should be saturated (ponded) with clean water for 24 hours before grouting. Remove water immediately before application.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.

- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

CONSTRUCTION GROUT

WARNING!

Construction Grout contains silica, crystalline quartz; portland cement; limestone; calcium oxide; gypsum; silica, amorphous.

Risks

Product is alkaline on contact with water and may cause injury to skin or eyes. Ingestion or inhalation of dust may cause irritation. Contains small amount of free respirable quartz which has been listed as a suspected human carcinogen by NTP and IARC. Repeated or prolonged overexposure to free respirable quartz may cause silicosis or other serious and delayed lung injury.

Precautions

Avoid contact with skin, eyes and clothing. Prevent inhalation of dust. Wash thoroughly after handling. Keep container closed when not in use. DO NOT take internally. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Waste Disposal Method

This product when discarded or disposed of is not listed as a hazardous waste in federal regulations. Dispose of in a landfill in accordance with local regulations. For additional information on personal protective equipment, first aid, and emergency procedures, refer to the product Material Safety Data Sheet (MSDS) on the job site or contact the company at the address or phone numbers given below.

Proposition 65

This product contains material listed by the State of California as known to cause cancer, birth defects or other reproductive harm.

VOC Content

0 g/L or 0 lbs/gal less water and exempt solvents.

For medical emergencies only, call ChemTrec (1-800-424-9300).

BASF Construction Chemicals, LLC – Building Systems

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517

Technical Service 800-243-6739



LIMITED WARRANTY NOTICE: Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1019296 6/09

Printed on recycled paper including 10% post-consumer fiber.

© 2009 BASF

Printed in U.S.A.